

PRODUCT DATA

Date: August 2010

Code: 01173/31

BOSTIK BOND-FLEX 300 LMN SILICONE SEALANT

Bostik Bond-Flex 300 LMN Silicone Sealant is a single part, low modulus, neutral curing silicone rubber sealant. It cures on exposure to atmospheric moisture to form a resilient highly elastic seal which maintains flexibility over a wide range of temperatures. Unlike many silicone sealants Bostik Bond-Flex 300 LMN has low odour when curing. The sealant is extremely resistant to weathering, ageing and water. Bostik Bond-Flex 300 LMN Silicone Sealant is suitable for sealing most building, construction and glazing joints. It can be used to seal assemblies of glass, glazed surfaces, aluminium and many other metals, uPVC and painted wood. Bostik Bond-Flex 300 LMN conforms to ISO 11600 F12, 5E.

Features

- Low odour – neutral cure
- Sealing metal cladding panels and curtain walling
- Permanent flexible seal
- Flexible at low (-40°C) and high temperatures (+100°C)
- Suitable for alkaline substrates such as concrete, mortar and cement.

Tensile strength 1.20 MPa

Elongation at break 480%

Modulus 100% elongation 0.35 MPa

Shore A hardness 17

Solvent for cleaning up White spirit

Product Characteristics

Colour	White & clear
Form	Non-slump paste
Specific gravity (density)	0.986 g/cm ³
Composition	Silicone rubber
Packaging	Cartons of 25 x C20 plastic cartridges
Shelf life/storage	At least 9 months from date of manufacture when stored unopened in a cool, dry place within the temperature range +5°C to +25°C and out of direct sunlight. PROTECT FROM FROST

Directions for use

IMPORTANT

Before embarking on any work involving Bostik Bond-Flex 300 LMN Silicone Sealant, the separate Safety Data Sheet should be carefully studied by those carrying out the work.

1. Surfaces should be clean, dry, firm and free from dust, oil, grease and any loose materials.

Do not clean PVC-u profiles with acetone or similar solvents. Loose and flaking paint should be thoroughly removed before sealing. As paint surfaces vary considerably, it is recommended that a preliminary adhesion test should be carried out before application.

2. If required place masking tape along joint edges and remove within 5 minutes of applying the sealant.
3. Cut off the dome at the top of the cartridge, cut the nozzle to the required diameter and then screw it onto the cartridge.
4. Insert the cartridge into a skeleton gun and squeeze the trigger until the sealant appears.
5. Apply ensuring no air is trapped behind the sealant.

NOTE: For conventional construction joints subject to movement, it is important that the dimensional proportions of the joint are correct. For Bostik Bond-Flex 300 LMN:

Width: *Minimum* 4mm
Maximum 25mm

Depth: *Minimum* 5mm
Maximum 12mm

Ideally the width of the joint should be twice the depth of the joint.

Typical Performance Data (approx.)

Drying time	<i>Touch:</i> 10 – 25 minutes <i>Through:</i> 24 hours (dependent on bead size and humidity – rate of cure is approx 1.5mm a day at 23°C/55% RH)
Service temperature	-45°C to +100°C
Application temperature	+5°C to +40°C
Coverage	10 linear metres of 6mm diameter bead per cartridge
Joint movement Accommodation	±25%

See final page for disclaimer.

Bostik Limited, Common Road, Stafford, ST16 3EH, England

Tel: +44 (0)1785 272727

Fax: +44 (0)1785 257898

www.bostik.co.uk

When using Bostik Bond-Flex 300 LMN for sealing typical expansion joints a suitable inert filling material such as closed cell polythene foam should be used to prevent sealant adhesion to the bottom of the joint, thus avoiding excess tension of the sealant.

6. The sealant surface can be tooled immediately to a smooth finish using a tooling stick or trowel dipped in diluted detergent.
7. Clean application equipment and remove excess uncured sealant with white spirit and cured sealant by abrasion.

Restrictions on Use

Bostik Bond-Flex 300 LMN is not suitable for use in areas subject to high abrasion. It also is not suitable for use on polyethylene, polypropylene, Teflon and bituminous or wax containing surfaces.

Bostik Bond-Flex 300 LMN may be discoloured in contact with organic elastomers such as EPDM and neoprene.

Bostik Bond-Flex 300 LMN is not recommended for sealing of aquaria or for continuous water immersion, or for structural glazing.

Precautions in Use

For health and safety instruction, first aid measures and spillage and disposal instructions, see separate health and safety data sheet for Bostik Bond-Flex 300 LMN Silicone Sealant.

Disclaimer - please read carefully

This disclaimer is issued by Bostik Limited ("the Company") and applies to the use of any products supplied by the Company ("the Products") displayed on this Technical Data Sheet ("TDS"). Please read this disclaimer carefully before using any of the Products. Using this TDS and/or the Product constitutes your acceptance of this disclaimer. Its contents shall prevail over any directions of use and any disclaimer and/or exclusion or limitation of liability of the Company which may appear on the packaging of the Products.

This disclaimer sets out the entire financial liability of the Company (including any liability for the acts or omissions of its employees, agents and sub-contractors) to any user of the Products ("Product User") in respect of any use made or resale by the Product User, of any of the Products in this TDS.

This disclaimer does not affect the Company's liability for death or personal injury arising from the Company's negligence in respect of the Products, nor its liability for fraud, or fraudulent misrepresentation, nor any other liability which cannot be excluded or limited under applicable law.

The Company's total liability however arising and whether caused by tort (including negligence and breach of statutory duty), breach of contract or otherwise, arising in connection with the use made or resale by the Product User of any of the Products in this TDS shall be limited to the price paid for the Product by the Product User.

The Company shall not be liable to the Product User for any pure economic loss, loss of profit, loss of business, depletion of goodwill or otherwise, in each case whether direct, indirect or consequential, or any claims (including in respect of personal injury insofar as not caused by the Company's negligence) for consequential compensation whatsoever (howsoever caused) which arise out of or in connection with the use made or resale by the Product User of any of the Products in this TDS.

The Company shall not be liable to the Product User in relation to any loss for any use which is inappropriate or use which is otherwise than in accordance with the relevant instructions for use of the Products in this TDS or on the Product. Product Users are advised to confirm the suitability of the Products by their own tests.

This TDS covers just one of a large range of products supplied by the Company. Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This TDS supersedes all previous TDSs relating to the Products, and users of it must ensure that it is the current issue. Destroy all previous TDS, and if in any doubt, contact the Company, quoting the code number in the top right hand corner on the front of this document.

Bostik Limited, Common Road, Stafford, ST16 3EH, England

Tel: +44 (0)1785 272727

Fax: +44 (0)1785 257898

www.bostik.co.uk